

Technical Data

INTEX HB



Product description

Intex HB is a styrene acrylic based product specially formulated to form coarse texture.

Recommended use

It is suitable for interior surfaces of concrete and cement plaster, wooden board, previously painted surfaces etc.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	300	500	800
Film thickness, wet (μm)	500	835	1335
Theoretical spreading rate (m^2/l)	1.15	0.70	.45

Physical properties

Colour	Off White
Solids (vol %)*	60 \pm 2
Specific Gravity	1.73-1.80

Surface preparation

The substrate must be sound, clean, dry, free from dust, oil, grease and laitance etc. All traces of release agents must be removed. On chalky and dusty surfaces, all loose material must be removed by stiff bristle brushing.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be min. 10°C and min. 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate.

Application methods

Roller or Hopper Gun

Application data

Mixing ratio (volume)	Single pack.
Thinner/Cleaner	Water

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate
- * Relative humidity 70%

Substrate temperature	23°C	35°C	45°C
Surface dry	3 h	2 h	1 h
Through dry	8 h	7 h	6 h
Dry to recoat, minimum	8 h	7 h	6 h

Dry to recoat, maximum

1. Recommended data given for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied – reference is made to the corresponding system data sheet.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotashield Alkali Resistant Primer OR Masonry Primer	1 coat
Intex HB	1 coat
Any Jotun emulsion topcoat	2 Coats

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. The product must be kept in a cool and well-ventilated place, protected from heat and direct sunlight. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

25 KGs

Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Jeddah - Head Office
Jotun Saudia CO. LTD
P.O. Box 34698
Jeddah 21478
Saudi Arabia
Phone +966 02 6350535
Fax +966 02 6362483

Riyadh - Branch
Jotun Saudia CO. LTD
P. O. Box 91586
Riyadh 11643
Saudi Arabia
Phone +966 01 2430503
Fax +966 01 2709689

Dammam - Branch
Jotun Saudia CO. LTD
P. O. Box 4906
Dammam 31412
Saudi Arabia
Phone +966 03 8473090
Fax +966 03 8474097

Yanbu - Factory
Jotun Saudia CO. LTD
P. O. Box 30154
Yanbu Al Sinaiyah
Saudi Arabia
Phone +966 04 3962911
Fax +966 04 3968483

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED MARCH 2005 BY JOTUN SAUDIA CO. LTD
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED

PDF Version :

