

Condition during application

The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. The moisture content in the concrete should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

Application methods

Brush Recommended
Roller Recommended

Application data

Mixing ratio (volume) 2 parts Comp. A (base) to be mixed thoroughly with 1 part Comp. B (curing agent). NO PART MIXING

Pot life (23°C) Jotafloor Solvent Free Primer Comp. B (20) 10 min. (30 min. after poured on to the floor).
Jotafloor Solvent Free Primer Comp. B (40) 20 min. (45 min. after poured on to the floor).

Thinner/Cleaner Jotun Thinner No. 17

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	15°C	23°C	40°C
Surface dry	7 h	5 h	3 h
Through dry	25 h	16 h	9 h
Cured	10 d	7 d	4 d
Dry to recoat, minimum	24 h	15 h	6 h
Dry to recoat, maximum ¹	72 h	48 h	30 h
Curing agent comp. B (40):			
Substrate temperature	15°C	23°C	40°C
Surface dry	12 h	10 h	6 h
Through dry	42 h	30 h	18 h
Cured	12 d	9 d	3 d
Dry to recoat, minimum	32 h	24 h	10 h
Dry to recoat, maximum ¹	96 h	72 h	36 h

1. The surface should be free from chalking and contamination prior to application. If the maximum dry to recoat time is exceeded, please contact Jotun Paints for advice.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Jotafloor Solvent Free Primer	1 - 2 x 100 µm	(Dry Film Thickness)
Jotafloor SL Universal	1 x 2000 µm	(Dry Film Thickness)
or		
Jotafloor Solvent Free Primer	1 - 2 x 100 µm	(Dry Film Thickness)
Jotafloor Topcoat	1 - 2 x 50 µm	(Dry Film Thickness)

Note: Thickness of the finished system will vary depending on use of the finished floor. Consult your local Jotun Office for advice.

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

2.6 l Comp. A (base) and 1.3 l Comp. B (curing agent).
Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Head Office & Nordic	Europe	Middle East	South East Asia
Jotun A/S	Jotun Paints (Europe) Ltd.	Jotun U.A.E Ltd. LLC.	Jotun (Singapore) Pte. Ltd.
P.O. Box 2021	Stather Road, Flixborough		No 11-15, Sixth Lok Yang
N-3248 Sandefjord	North Lincolnshire DN15	Al Quoz Industrial Area	Road
Norway	8RR	P.O Box 3671	Jurong
Phone +47 33 45 70 00	United Kingdom	Dubai U.A.E	Singapore 628 111
Fax +47 33 46 46 13	Phone +44 172 44 00 000	Phone +971 4 3 39 50 00	Phone +65 6265 4711
	Fax +44 172 44 00 100	Fax +971 4 3 38 06 66	Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 1 APRIL 2003 BY JOTUN

THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED