

Technical Data

JOTASHIELD S.A SILK



Product description

Jotashield S.A Silk is high quality acrylic copolymer based emulsion paint with outstanding washability, hiding power and colour retention properties. It has a good flow and gives a smooth, durable Silk finish. Ideal for exterior surfaces

Recommended use

For use on exterior surfaces, i.e. cement plaster, stucco filler, gypsum boards, concrete, asbestos cement sheeting and rendered block work. This product has excellent weather and high scrub resistance.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (μm)	30	50	30
Film thickness, wet (μm)	70	113	70
Theoretical spreading rate (m^2/l)	14.6	8.8	14.6

Comments

The theoretical spread rate has been calculated for the below stated volume solids and dry film thickness. The practical spreading rate will depend on the actual dry film thickness, the nature of the substrate and the application method.

Physical properties

Colour	As per emulsion colourcard , recommended NCS exterior shades from Jotun Multicolor Tinting machine.
Solids (vol %)	44 \pm 2
Solids (weight %)	Min.50
Specific Gravity	1.25-1.40
Flexibility	Good
Gloss	Silk
Water resistance	Very Good
Flash Point	Non-Flammable

Surface preparation

The substrate must be sound, clean, dry, free from dust, oil, grease and laitance etc. All traces of release agents must be removed. On chalky and dusty surfaces, all loose material must be removed by stiff bristle brushing.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be min. 10°C and min. 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate.

Application methods

Spray	Airless or conventional spray.
Brush	Recommended.
Roller	Recommended.

Application data

Mixing ratio (volume)	Single pack.
Thinner/Cleaner	Water
Guiding data airless spray	
Pressure at nozzle	min. 150 kg./cm ² (2100 p.s.i.)
Nozzle tip	0.018" - 0.021"
Spray angle	40° - 80°
Filter	Check to ensure that filters are clean.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate
- * Relative humidity 70%

Substrate temperature	23°C	35°C
Surface dry	30 min.	15 min.
Through dry	2.3 h	1 h
Dry to recoat, minimum	6 h	4 h

Dry to recoat, maximum

1. Recommended data given for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied – reference is made to the corresponding system data sheet.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

On Porous and chalking surfaces

Jotashield Penetrating Primer	1 coat
Jotun Block Filler	2 coats
Jotashield S.A Silk	2 coats

On New and old surfaces

Jotashield Alkali Resistant Primer	1 coat
Jotun Block Filler	2 coats
Jotashield S.A Silk	2 coats

Exterior - Please refer to the Decorative Sales Department for technical advice.

Storage

The product must be stored in accordance with national regulations. The product must be kept in a cool and well-ventilated place, protected from heat and direct sunlight. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

1 L, 1 US G and 18 Liter.

Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Jeddah - Head Office
Jotun Saudia CO. LTD
P.O. Box 34698
Jeddah 21478
Saudi Arabia
Phone +966 02 6359535
Fax +966 02 6362483

Riyadh - Branch
Jotun Saudia CO. LTD
P. O. Box 91586
Riyadh 11643
Saudi Arabia
Phone +966 01 2430503
Fax +966 01 2709689

Dammam - Branch
Jotun Saudia CO. LTD
P. O. Box 4906
Dammam 31412
Saudi Arabia
Phone +966 03 8473090
Fax +966 03 8474097

Yanbu - Branch
Jotun Saudia CO. LTD
P. O. Box 30154
Yanbu Al Sinaiyah
Saudi Arabia
Phone +966 04 3962911
Fax +966 04 3968483

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED MARCH 2005 BY JOTUN SAUDIA CO. LTD
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED

PDF Version :

