

Technical Data

JOTUN WOODSHIELD STAIN



Product description

Jotun WoodShield Stain is a high quality wood stain based on a special Penetrating Alkyd oil. It penetrates deep into the wood and ensures effective and lasting protection against sunlight, rain, microbiological growth and termite attack.

Recommended use

For interior and exterior on all kinds of untreated hardwood, softwood, plywood, chip board, etc. in combination with woodshield varnish or alone if sufficient film thickness is obtained. Can also be used on wood previously treated with other wood protections.

Film thickness and spreading rate

	Minimum	Maximum
Film thickness, dry (μm)		Penetrating
Film thickness, wet (μm)		Penetrating
Theoretical spreading rate (m^2/l)	10.0	15.0

Physical properties

Colour	10 Standard colours. Can also be tinted in Multicolor tinting system.
Solids (vol %)*	11 \pm 2
Flash point	39°C \pm 2 (Setaflash)
Specific Gravity	0.85 – 0.89
Water Resistance	Good
UV Resistance	Good
Flexibility	Good

Surface preparation

The Surface must be clean, dry, knots must be degreased with Jotun Lacquer Thinner and exposed wood must be sanded to reach a sound surface.

Condition during application

The temperature of the substrate should be min. 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate.

Application methods

Brush Recommended.

Application data

Mixing ratio (volume)	Single pack.
Thinner/Cleaner	Jotun Thinner No. 2

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	23°C	35°C
Surface dry	1.5-2 h	1 h
Through dry	10 h	6 h
Dry to recoat, minimum	6 h	4 h
Dry to recoat, maximum	48 h	36 h

1. Recommended data given for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied – reference is made to the corresponding system data sheet.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

INTERIOR

System 1

Jotun Woodshield Stain* 2 coats

System 2

Jotun Woodshield Stain* 2 coats

Jotun Woodshield Varnish Clear 1 coat

* If anti-termite protection is required, use Jotun Wood Preserver as the first coat

EXTERIOR

System 1

Jotun Wood Preserver 1 coat

Jotun Woodshield Stain* 2 coats

System 2

Jotun Wood Preserver 1 coat

Jotun Woodshield Stain* 2 coats

Jotun Woodshield Varnish Clear 1 coat

* Jotun Woodshield stain must never be used untinted.

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. The product must be kept in a cool and well-ventilated place, protected from heat and direct sunlight. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

0.9 L and 3.6 L.

Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Jeddah - Head Office	Riyadh - Branch	Dammam - Branch	Yanbu - Factory
Jotun Saudia CO. LTD	Jotun Saudia CO. LTD	Jotun Saudia CO. LTD	Jotun Saudia CO. LTD
P.O. Box 34698	P. O. Box 91586	P. O. Box 4906	P. O. Box 30154
Jeddah 21478	Riyadh 11643	Dammam 31412	Yanbu, Al Sinaiyah
Saudi Arabia	Saudi Arabia	Saudi Arabia	Saudi Arabia
Phone +966 02 6350535	Phone +966 01 2430503	Phone +966 03 8473090	Phone +966 04 3962911
Fax +966 02 6362483	Fax +966 01 2709689	Fax +966 03 8474097	Fax +966 04 3968483

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED MARCH 2005 BY JOTUN SAUDIA CO LTD
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED